



Corporate Office : 607, CORPORATE AVENUE, SONAWALA ROAD, GOREGAON (E), MUMBAI - 400 063

Warehouse : At Orsun Ceramic Zone, Near Bhabha Ceramic, City -Lakhdirpur,
Taluka - Morbi, District - Rajkot, Gujrat.

TEL : 022 - 26861593 & TELEFAX - 022 - 26861693

EMAIL ID : office@mahekenterprise.com, mahekenterprise2007@gmail.com

WEBSITE : www.mahekenterprise.com

Specifications of Mid Alumina Balls

Composition	Al ₂ O ₃ (%)	≥ 68
	SiO ₂ (%)	≤ 23.6
	MgO	≤ 2.2
	Fe ₂ O ₃	≤ 1.1
	KOH + NaO	≤ 3.7
	CaO	≤ 0.45
	TiO ₂	≤ 0.08
Water Absorption rate (%)	0.01 Max	
Bulk Density (gr/cm ³)	2.96;2.98;2.96;2.95;2.97 (Avg : 2.96)	
Hardness (Mohs)	≥ 7	
Self Wearing rate (24h's)	≤ 0.15	
Compressive Strength (Mohs)	≥ 1700	
Colour	Beige	

Dimension	30	40	50	60	70
Diameter (mm)	30 ± 1	40 ± 1	50 ± 2	60 ± 2	70 ± 3

MR. KINJAL DOSHI -

+91 9821268669